

In re Application of: Yair Ein-Eli et al.  
Serial No.: 10/551,714  
Filed: July 20, 2006  
Office Action Mailing Date: May 13, 2010

Examiner: PARVINI, Pegah  
Group Art Unit: 1793  
Confirmation No. 6188  
Attorney Docket: 30579

**In the claims:**

**Please amend the claims as follows:**

1. (Previously presented) A composition ~~useful for the formation of a passivating layer on a surface, the surface including more than 5% copper by weight, the composition~~ comprising a solution which has a pH that ranges from 9 to 13 and is being devoid of a film-forming agent, a copper complexing agent and ammonium cations, the composition is being such that when it is applied to a surface which includes more than 5 % copper by weight, it oxidizes ~~having an oxidation potential sufficient to oxidize the surface~~ copper to form copper oxides ~~and being devoid of a film forming agent, a copper complexing agent and ammonium cations, wherein neither said copper nor said copper oxides are soluble in the composition, the composition being useful for the formation of a passivating layer on said surface.~~

2. (Previously presented) The composition of claim 1, wherein the surface includes more than 10% copper by weight.

3. (Previously presented) The composition of claim 1, wherein the surface includes more than 20% copper by weight.

4. (Previously presented) The composition of claim 1, wherein the surface includes more than 40% copper by weight.

5. (Previously presented) The composition of claim 1, wherein the surface includes more than 50% copper by weight.

6. (Previously presented) The composition of claim 1, wherein the surface includes more than 80% copper by weight.

7. (Previously presented) The composition of claim 1, wherein said oxidation potential is lower than  $P_{pH}$  volt relative to a saturated calomel reference electrode, where

$$P_{pH} = -0.05 \times pH + 0.425$$

pH being said pH of the composition.

8. (Previously presented) The composition of claim 1, wherein said pH is between 9 and 10 and said oxidation potential is lower than -0.05 volt relative to a saturated calomel reference electrode.

9. (Previously presented) The composition of claim 1, wherein said pH is between 10 and 11 and said oxidation potential is lower than -0.1 volt relative to a saturated calomel reference electrode.

10. (Previously presented) The composition of claim 1, wherein said pH is between 11 and 12 and said oxidation potential is lower than -0.15 volt relative to a saturated calomel reference electrode.

11. (Previously presented) The composition of claim 1, wherein said pH is between 12 and 13 and said oxidation potential is lower than -0.2 volt relative to a saturated calomel reference electrode.

12. (Previously presented) The composition of claim 1, wherein said oxidation potential is lower than a saturated calomel reference electrode by an oxidation potential selected from the group consisting of -0.2 volt, -0.15 volt, -0.10 volt, -0.05 volt, 0.0 volt, 0.05 volt, 0.10 volt, 0.15 volt, 0.20 volt, 0.25 volt, 0.3 volt, 0.35 volt, 0.40 volt, 0.45 volt, 0.50 volt, 0.55 volt, 0.60 volt, 0.65 volt and 0.7 volt.

12.5. (canceled)

In re Application of: Yair Ein-Eli et al.  
Serial No.: 10/551,714  
Filed: July 20, 2006  
Office Action Mailing Date: May 13, 2010

Examiner: PARVINI, Pegah  
Group Art Unit: 1793  
Confirmation No. 6188  
Attorney Docket: 30579

13. (Original) The composition of claim 1, comprising
  - a) a cation selected from the group of alkaline metal cations and alkaline earth metal cations; and
  - b) an anion of a weak acid.
14. (Original) The composition of claim 13, wherein said cation is selected from the group consisting of  $\text{Li}^+$ ,  $\text{Na}^+$ ,  $\text{K}^+$ ,  $\text{Rb}^+$ ,  $\text{Cs}^+$ ,  $\text{Be}^{2+}$ ,  $\text{Mg}^{2+}$ ,  $\text{Ca}^{2+}$ ,  $\text{Sr}^{2+}$  and  $\text{Ba}^{2+}$ .
15. (Previously presented) The composition of claim 13, wherein said weak acid has a pKa greater than 0.
16. (Original) The composition of claim 13, wherein said anion is selected from the group consisting of acetate, adipate, bicarbonate, bisulfate, carbonate, chloroacetate, citrate, crotonate, cyanate, glutarate, dihydrogen phosphate, hydrogen phosphate, hydrogen sulfate, hydroxide, d-lactate, l-lactate, d-malate, l-malate, maleate, d-mandelate, l-mandelate, malonate, oxalate, permanganate, phosphate, hydrogen phthalate, phthalate, propanoate, succinate, sulfanilate, sulfate, d-tartarate and l-tartarate.
17. (Original) The composition of claim 13, wherein said cation is  $\text{K}^+$  and said anion is carbonate.
18. (Original) The composition of claim 13, wherein said cation is  $\text{Cs}^+$  and said anion is carbonate.
19. (Original) The composition of claim 13, further comprising an oxidizing agent.
20. (Original) The composition of claim 19, wherein said oxidizing agent is selected from the group consisting of phenols, peroxides, permanganates, chromates, iodates, iron salts, aluminum salts, sodium salts, potassium salts, phosphonium salts, chlorates, perchlorates, persulfates and mixtures thereof.

In re Application of: Yair Ein-Eli et al.  
Serial No.: 10/551,714  
Filed: July 20, 2006  
Office Action Mailing Date: May 13, 2010

Examiner: PARVINI, Pegah  
Group Art Unit: 1793  
Confirmation No. 6188  
Attorney Docket: 30579

21. (Original) The composition of claim 19, wherein said oxidizing agent is selected from the group consisting of phenol,  $\text{KMnO}_4$ ,  $\text{KIO}_3$ ,  $\text{KBrO}_3$ ,  $\text{K}_3\text{Fe}(\text{CN})_6$ ,  $\text{K}_2\text{Cr}_2\text{O}_7$ ,  $\text{V}_2\text{O}_3$ ,  $\text{H}_2\text{O}_2$ ,  $\text{HOCl}$ ,  $\text{KOCl}$  and  $\text{KMgO}_4$ .

22. (Original) The composition of claim 19, wherein said oxidizing agent is  $\text{KMnO}_4$ .

23-25. (Canceled)

26. (Original) The composition of claim 1, comprising abrasive particles.

27. (Original) The composition of claim 26, wherein said abrasive particles are metal oxides.

28. (Original) The composition of claim 27, wherein said metal oxide is selected from the group consisting of oxides of aluminum, cerium, germanium, silicon, titanium, zirconium and mixtures thereof.

29. (Original) The composition of claim 26, wherein said abrasive particles are chosen from the group comprising  $\text{SiO}_2$ ,  $\text{CeO}_2$ ,  $\text{Al}_2\text{O}_3$ ,  $\text{SiC}$ ,  $\text{Si}_3\text{N}_4$  and  $\text{Fe}_2\text{O}_3$ .

30. (Previously presented) The composition of claim 26, wherein said abrasive particles comprise between 1% and 30% by weight of the composition.

31. (Withdrawn) A method of forming a passivating layer on a surface, the surface including more than 5% copper by weight, the method comprising contacting the surface with the composition of claim 1.

32. (Withdrawn) The method of claim 31, wherein said surface includes more than 10% copper by weight.

In re Application of: Yair Ein-Eli et al.  
Serial No.: 10/551,714  
Filed: July 20, 2006  
Office Action Mailing Date: May 13, 2010

Examiner: PARVINI, Pegah  
Group Art Unit: 1793  
Confirmation No. 6188  
Attorney Docket: 30579

33. (Withdrawn) The method of claim 31, wherein said surface includes more than 20% copper by weight.

34. (Withdrawn) The method of claim 31, wherein said surface includes more than 40% copper by weight.

35. (Withdrawn) The method of claim 31, wherein said surface includes more than 50% copper by weight.

36. (Withdrawn) The method of claim 31, wherein said surface includes more than 80% copper by weight.

37. (Withdrawn) A method for the preparation of a composition useful for the formation of a passivating layer on a surface, the surface including more than about 5% copper by weight, comprising preparing a solution having a pH equal to or greater than about 9 and having an oxidation potential sufficient to oxidize the surface to form copper oxides, wherein neither copper nor said copper oxides are substantially soluble in the composition.

38. (Withdrawn) The method of claim 37, wherein said oxidation potential is more positive than a saturated calomel reference electrode by an oxidation potential selected from the group consisting of -0.2V, -0.15V, -0.10V, -0.05V, 0.0V, 0.05V, 0.10V, 0.15V, 0.20V, 0.25V, 0.3V, 0.35V, 0.40V, 0.45V, 0.50V, 0.55V, 0.60V, 0.65V and 0.7V.

38.5. (canceled)

39. (Withdrawn) The method of claim 37, comprising

a) providing a solution comprising water;

b) adding to said solution a cation selected from the group consisting of alkaline metal cations and alkaline earth metal cations and an anion of a weak acid in an amount so that the pH of said solution is equal to or greater than about 9; and

c) adding to said solution an oxidizing agent so that the oxidation potential of said solution is more positive than about  $P_{pH}$  V relative to a saturated calomel reference electrode, where

$$P_{pH} = -0.05 \times pH + 0.425$$

pH being the pH of said solution.

40. (Withdrawn) The method of claim 39, wherein said oxidizing agent is selected from the group consisting of phenols, peroxides, permanganates, chromates, iodates, iron salts, aluminum salts, sodium salts, potassium salts, phosphonium salts, chlorates, perchlorates, persulfates and mixtures thereof.

41. (Withdrawn) The method of claim 37, further comprising adding abrasive particles to said solution.

42. (Withdrawn) The method of claim 41, wherein said abrasive particles are metal oxides.

43. (Withdrawn) The method of claim 42, wherein said metal oxide is selected from the group consisting of oxides of aluminum, cerium, germanium, silicon, titanium, zirconium and mixtures thereof.

44. (Withdrawn) The method of claim 41, wherein said abrasive particles are chosen from the group comprising  $SiO_2$ ,  $CeO_2$ ,  $Al_2O_3$ , SiC,  $Si_3N_4$  and  $Fe_2O_3$ .

45. (Withdrawn) The method of claim 41, wherein said abrasive particles comprise between about 1% and 30% by weight of said solution.

46. (Withdrawn) A method of forming a passivating layer on a surface, the surface including more than about 5% copper by weight, comprising contacting the surface with a composition of claim 1.

47. (Withdrawn) A method for planarizing a surface, the surface including more than about 5% copper by weight, comprising abrading the surface in the presence of a composition of claim 1.

48. (Withdrawn) The method of claim 37, wherein the surface includes more than about 10% copper by weight.

49. (Withdrawn) The method of claim 37, wherein the surface includes more than about 20% copper by weight.

50. (Withdrawn) The method of claim 37, wherein the surface includes more than about 40% copper by weight.

51. (Withdrawn) The method of claim 37, wherein the surface includes more than about 50% copper by weight.

52. (Withdrawn) The method of claim 37, wherein the surface includes more than about 80% copper by weight

53. (Previously presented) The composition of claim 12, wherein said oxidation potential is lower than a saturated calomel reference electrode by an oxidation potential of at least 0.0 volt.

54. (Withdrawn) The method of claim 38, wherein said oxidation potential is more positive than a saturated calomel reference electrode by an oxidation potential of at least 0.0V.

55. (Previously Presented) The composition of claim 1, consisting of:  
a) a cation selected from the group of alkaline metal cations and alkaline earth metal cations;  
b) an anion of a weak acid;

In re Application of: Yair Ein-Eli et al.  
Serial No.: 10/551,714  
Filed: July 20, 2006  
Office Action Mailing Date: May 13, 2010

Examiner: PARVINI, Pegah  
Group Art Unit: 1793  
Confirmation No. 6188  
Attorney Docket: 30579

- c) abrasive particles; and
- d) an oxidizing agent.

56. (Previously Presented) The composition of claim 55, wherein said cation is selected from the group consisting of  $\text{Li}^+$ ,  $\text{Na}^+$ ,  $\text{K}^+$ ,  $\text{Rb}^+$ ,  $\text{Cs}^+$ ,  $\text{Be}^{2+}$ ,  $\text{Mg}^{2+}$ ,  $\text{Ca}^{2+}$ ,  $\text{Sr}^{2+}$  and  $\text{Ba}^{2+}$ .

57. (Previously Presented) The composition of claim 55, wherein said weak acid has a pKa greater than 0.

58. (Previously Presented) The composition of claim 55, wherein said oxidizing agent is selected from the group consisting of phenols, peroxides, permanganates, chromates, iodates, iron salts, aluminum salts, sodium salts, potassium salts, phosphonium salts, chlorates, perchlorates, persulfates and mixtures thereof.

59. (Previously Presented) The composition of claim 55, wherein said abrasive particles are metal oxides.